

## Formaterm® ABS/ASA

### Product characteristics

- High vacuum forming properties
- Excellent weather resistance
- Very high impact strength and rigidity

### Typical field of application

- Vacuum forming techniques

	Test method	Unit	Value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	1,03
Water absorption	DIN EN ISO 62	%	0,7
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	45
Elongation at break	DIN EN ISO 527	%	10
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2300
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m <sup>2</sup>	35
Shore hardness	DIN EN ISO 868	scale D	75
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	-
Thermal conductivity	DIN 52612-1	W / (m * K)	0,18
Thermal capacity	DIN 52612	kJ / (kg * K)	-
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	60-110
Service temperature, long term	Average	°C	-40 ... 75
Service temperature, short term (max.)	Average	°C	-
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	98
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		3,40
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,025
Volume resistivity	IEC 60093	Ω *cm	>10 <sup>15</sup>
Surface resistivity	IEC 60093	Ω	>10 <sup>13</sup>
Comparative tracking index	IEC 60112		-
Dielectric strength	IEC 60243	kV/mm	20

The data mentioned in this brochure are average values ascertained by current statistical returns and tests. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.