

## Polystone® G natural AST

### Product characteristics

- Antistatic
- Easy processing
- Excellent weldability

### Typical field of application

- Clean room and semiconductor technology

	Test method	Unit	Value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	23
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	800
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m <sup>2</sup>	12
Shore hardness	DIN EN ISO 868	scale D	63
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	133 - 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	150-230
Service temperature, long term	Average	°C	-50 ... 80
Service temperature, short term (max.)	Average	°C	100
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	67
<b>Electrical properties</b>			
Volume resistivity	IEC 60093	Ω *cm	-
Surface resistivity	IEC 60093	Ω	>10 <sup>9</sup> ... 10 <sup>12</sup>

The data mentioned in this brochure are average values ascertained by current statistical returns and tests. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.