



SUSTARIN C MG • New Materials for medical technology

tested on the semi-finished product acc. to USP Class VI & ISO 10993-5

In addition to the excellent properties of the well known SUSTARIN C, the new SUSTARIN C MG product group offers a certified biocompatibility according to **USP Class VI** and **DIN EN ISO 10993-5** (cytotoxicity). In order to meet the requirements of the medical technology market, tests for the biocompatibility were carried out on the semi-finished product.



Production possibilities

	Ø mm	Length mm	Colour
Rods	5 - 300	1.000/2.000/3.000	

Stock items are available in various dimensions (25-65 mm).
Sheets, plates, etc. upon request.

Technical characteristics (extract)

Properties	Unit	Test standard	Value
DIN specification		DIN EN ISO 1043-1	POM-C
Density	g/cm ³	DIN EN ISO 1183-1	1,41
Yield stress/tensile strength	MPa	DIN EN ISO 527	65
Elongation at break	%	DIN EN ISO 527	30
E-modulus/stiffness	MPa	DIN EN ISO 527	2.600
Notched impact strength (charpy)	kJ/m ²	DIN EN ISO 179	5,5
Service temperature, short term	C°	Richtwert	140
Heat deflection temperature	C°	DIN EN ISO 75 (A)	110

The above specifications are in accordance with our latest state of information. They do not ensure any particular feature or suitability for applications.

Proven applications

Clamps for fixing medical hardware at the bedside



Certifications

- FDA conformity
- tested biocompatibility acc. to **USP Class VI** and **DIN EN ISO 10993-5** on the semi-finished product makes the approval of the medical device easier

Important properties

- multiple sterilization is possible with hot steam, plasma as well as ethylene oxide
- good resistance against many detergents, disinfectants and solvents
- ideal combination of hardness, stiffness and toughness
- optimized annealing process (semi-finished products have low material stresses) and the low water absorption lead to a high dimensional stability and precision of the machined parts
- pleasant haptics

Your contact

Norbert Hendel
Technical Marketing

Röchling Sustaplast KG
Sustaplast-Straße 1
D-56112 Lahnstein/Germany

Tel. +49 2621 693-154
Fax +49 2621 693-125
nhendel@sustaplast.de