

## Technical Data Sheet

# Sustamid<sup>®</sup> 66 MO (Extruded Nylon MoS2 Filled) -

## ASTM

PA 66

### Typical characteristics

- Good dimensional stability
- Good sliding properties
- High abrasion resistance

### Typical industries

- Aerospace
- Electrical Industry
- Mechanical Engineering Industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D792	g / cm <sup>3</sup>	1.15
Water Absorption	ASTM D570	%	8.5
Water Absorption 24 hours	ASTM D570	%	1.0
Dissipation Factor	ASTM D150	1MHz	0.02
<b>Mechanical properties</b>			
Tensile Strength at Yield	ASTM D638	psi	12000
Hardness	ASTM D2240	Shore D	85
Tensile Elongation	ASTM D638	%	25
Flexural Strength	ASTM D790	psi	17000
Flexural Modulus	ASTM D790	psi	460000
Compressive Strength	ASTM D695	psi	16000
Rockwell Hardness	ASTM D785	M	85
Rockwell Hardness	ASTM D785	R	115
Shear Strength	ASTM D732	psi	10500
Izod Impact, Notched	ASTM D256	ft-lb/in	0.6
Coefficient of Friction, Dynamic			0.23
<b>Thermal properties</b>			
Thermal Conductivity		in/hr/ft <sup>2</sup> /°F	1.7
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	4.0

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Melting Point	ASTM D789	°F	495
Continuous Service Temperature, Air		°F	220
Flammability, UL94		1/8 inch	HB
Deflection Temperature at 264psi	ASTM D648	°F	195
Deflection Temperature at 66psi	ASTM D648	°F	470
<b>Electrical properties</b>			
Dielectric constant	ASTM D150	1MHz	3.8
Dielectric strength	ASTM D149	V/mil	350
Surface resistivity	ASTM D257	Ω/cm	>10 <sup>13</sup>
<b>Compliance properties</b>			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Release: 26/12/2024 • Version: 2.0  
 PIM-ID: 774101 • PIM-Code: 30-16-153.223.63-8.11.5-2  
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

