

Technical Data Sheet

Fibracon[®] PTFE + 10% Ekonol

PTFE

Typical characteristics

- Good wear resistance
- Improved stability at high temperatures

Typical industries

- Construction de réservoirs et d'installations chimiques
- Construction de véhicules
- Industrie électronique
- Pétrole et gaz
- Construction de machines et d'installations
- Healthcare
- Industrie agroalimentaire
- L'énergie éolienne

	Test method	Unit	Guideline value
General properties			
Densité	ASTM D4894	g / cm ³	2.05
Mechanical properties			
Hardness	ASTM D2240	Shore D	58
Tensile Strength (23°C)	ASTM D4894	MPa	22
Elongation at Break	ASTM D4894	%	260
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 20/09/2023
 PIM-ID: 709603 • PIM-Code: 37-40-143.24-9.7.8.5.5.27.5.10-1
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

