

Technical Data Sheet

Polystone[®] P (Copolymer) PG + UV-stabilized beige

PP-C

Typical characteristics

- High mechanical strength
- Good weldability
- Good chlorine resistance
- UV-resistant

Typical industries

- Sport e tempo libero

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,92
Water absorption	DIN EN ISO 62	%	<0,1
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1200
Notched impact strength	DIN EN ISO 179	kJ / m ²	> 30
Shore hardness	DIN EN ISO 868	scale D	68
Thermal properties			
Melting temperature	ISO 11357-3	°C	162 – 167
Thermal conductivity	DIN 52612-1	W / (m * K)	0,20
Thermal capacity	DIN 52612	kJ / (kg * K)	1,70
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	120 - 190
Service temperature, long term	Average	°C	-30 ... 100
Service temperature, short term (max.)	Average	°C	150
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	85
Electrical properties			
Dielectric constant	IEC 60250		2,5
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,00019
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{13}$
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	45

Attention: Please see also product information

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/06/2026 • Release: 20/09/2023 • Version: 1.0
 PIM-ID: 718605 • PIM-Code: 46-8-23.16.10.15-3-8
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

