

## テクニカルデータシート

Polystone<sup>®</sup> P (Copolymer) PG + UV-stabilized beige

PP-C

## 製品の特徴

- 高い機械的強度
- 良好な溶接性
- Good chlorine resistance
- UV耐性

## 製品の用途例

- スポーツ・レジャー

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,92
吸水率	DIN EN ISO 62	%	<0,1
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
<b>機械的物性</b>			
引張降伏応力	DIN EN ISO 527	MPa	24
引張破壊伸び歪	DIN EN ISO 527	%	>50
引張弾性率	DIN EN ISO 527	MPa	1200
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m <sup>2</sup>	> 30
シヨア硬度	DIN EN ISO 868	scale D	68
<b>熱的物性</b>			
融点	ISO 11357-3	°C	162 – 167
熱伝導率	DIN 52612-1	W / (m * K)	0,20
熱容量	DIN 52612	kJ / (kg * K)	1,70
線膨張係数	DIN 53752	10 <sup>-6</sup> / K	120 - 190
使用温度 (長期)	平均値	°C	-30 ... 100
使用温度 (短期、最大)	平均値	°C	150
ピカットB軟化温度	DIN EN ISO 306, Vicat B	°C	85
<b>電気的物性</b>			
誘電率	IEC 60250		2,5
誘電正接 (10 <sup>6</sup> Hz)	IEC 60250		0,00019

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Release: 20/09/2023 • Version: 1.0

PIM-ID: 718605 • PIM-Code: 46-8-23.16.10.15-3-8

Company-IDs: 20000-1


Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
体積固有抵抗	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{14}$
表面固有抵抗	DIN EN 62631-3-2	$\Omega$	$>10^{13}$
比較トラッキング指数	IEC 60112		600
絶縁破壊電圧	IEC 60243	kV / mm	45

Attention: Please see also product information

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 718605 • PIM-Code: 46-8-23.16.10.15-3-8  
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

