

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 15% Glass

PTFE

### Typical characteristics

- FDA approved grades of glass filled PTFE are available
- Good wear properties
- Reduced deformation under load

### Typical industries

- Construction de réservoirs et d'installations chimiques
- Construction de véhicules
- Industrie électronique
- Pétrole et gaz
- Construction de machines et d'installations
- Healthcare
- Industrie agroalimentaire
- L'énergie éolienne

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	ASTM D4894	g / cm <sup>3</sup>	2.21
<b>Mechanical properties</b>			
Hardness	Needle	Shore D	60
Tensile Strength (23°C)	ASTM D4894	MPa	20
Elongation at Break	ASTM D4894	%	240
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Release: 20/09/2023  
 PIM-ID: 709607 • PIM-Code: 49-40-10.126.14-9.7.8.5.5.27.5.10-1  
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

