

Technical Data Sheet

Fibracon[®] PTFE + 20% PEEK

PTFE

Typical characteristics

- Good dimensional stability
- Good wear resistance

Typical industries

- Costruzione di serbatoi e impianti chimici
- Costruzione di veicoli
- Elettronica
- Olio e gas
- Ingegneria meccanica e impiantistica
- Healthcare
- Industria alimentare
- Energia eolica

	Test method	Unit	Guideline value
General properties			
Density	ASTM 4894	g / cm ³	1.92
Mechanical properties			
Hardness	Needle	Shore D	63
Tensile Strength (23°C)	ASTM 4894	MPa	16
Elongation at Break	ASTM 4894	%	230
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 20/09/2023
 PIM-ID: 709611 • PIM-Code: 35-40-153.143-9.7.8.5.5.27.5.10-1
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

