

### Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 23% Carbon+ 2% Graphite

PTFE

#### Typical characteristics

- Excelente para ambientes secos y mal lubricados.
- Good thermal conductivity
- Conducto electrico
- Deformación reducida bajo carga en comparación con el PTFE virgen

#### Typical industries

- Construcción de contenedores químico
- Construcción de vehículos
- Electrónica
- Petróleo y gas
- Construcción de máquinas e instalaciones
- Healthcare
- Industria alimentaria
- Energía eólica

|                              | Test method | Unit                | Guideline value |
|------------------------------|-------------|---------------------|-----------------|
| <b>General properties</b>    |             |                     |                 |
| Density                      | ASTM D4894  | g / cm <sup>3</sup> | 2.09            |
| <b>Mechanical properties</b> |             |                     |                 |
| Hardness                     | Needle      | Shore D             | 64 - 70         |
| Tensile Strength (23°C)      | ASTM D4894  | MPa                 | 18              |
| Elongation at Break          | ASTM D4894  | %                   | 65              |
| <b>Thermal properties</b>    |             |                     |                 |
| Service Temperature          |             | °C                  | -200 to +260    |

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Release: 20/09/2023  
 PIM-ID: 709613 • PIM-Code: 44-40-16.3.13.14-9.7.8.5.5.27.5.10-1  
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

