

### Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 23% Glass+ 2% MoS2

PTFE

#### Typical characteristics

- High hardness
- Lower co-efficient of friction than glass filled PTFE
- Reduced deformation under load

#### Typical industries

- Costruzione di serbatoi e impianti chimici
- Costruzione di veicoli
- Elettronica
- Olio e gas
- Ingegneria meccanica e impiantistica
- Healthcare
- Industria alimentare
- Energia eolica

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	ASTM D1457	g / cm <sup>3</sup>	2.2 - 2.4
<b>Mechanical properties</b>			
Hardness	ASTM D1706	Shore D	57 - 61
Tensile Strength (23°C)	ASTM D1457	N/mm <sup>2</sup>	>15
Elongation at Break	ASTM D1457*	%	>200
<b>Thermal properties</b>			
Service Temperature		°C	-200 to +260

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Release: 20/09/2023  
 PIM-ID: 709614 • PIM-Code: 36-40-11.13.14-9.7.8.5.5.27.5.10-2  
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

