

Technisches Datenblatt

Fibracon[®] PTFE + 25% Carbon filled

PTFE

Typische Eigenschaften

- Geringer Verschleiß bei Schmierung mit Wasser
- Reduzierte Verformung unter Last (verbesserte Druckfestigkeit)
- Verbesserte thermische und elektrische Leitfähigkeit

Typische Industrien

- Chemischer Anlagenbau
- Fahrzeugbau
- Elektronik
- Öl und Gas
- Maschinen- und Anlagenbau
- Healthcare
- Lebensmittelindustrie
- Windkraft

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
Bulk Density	ASTM D4894	g/l	600
Specific Gravity	ASTM D4894	-	2.1±0.03
Mechanische Eigenschaften			
Tensile Strength (Cross Direction)	ASTM D4894	MPa	Min.15
Elongation (Cross Direction)	ASTM D4894	%	Min.90
Ball Hardness	ISO 2039	MPa	45±2
Deformation Under Load	ASTM D621	%	5 - 7
Thermische Eigenschaften			
Gebrauchstemperaturbereich		°C	-200 to +260
Elektrische Eigenschaften			
Volume Resistivity	ASTM D257	Ωcm	10 ⁴

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 20/09/2023
 PIM-ID: 709615 • PIM-Code: 36-40-16.12.16-9.7.8.5.5.27.5.10-1
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

