

## Technical Data Sheet

# Fibracon<sup>®</sup> PTFE + 25% Ekonol

PTFE

### Typical characteristics

- Good wear resistance
- Improved stability at high temperatures

### Typical industries

- Chemical Processing Industry
- Vehicle Construction
- Electronics
- Oil and Gas
- Mechanical Engineering Industry
- Healthcare
- Food Industry
- Wind Energy

|                              | Test method | Unit                | Guideline value |
|------------------------------|-------------|---------------------|-----------------|
| <b>General properties</b>    |             |                     |                 |
| Density                      | ASTM D1457  | g / cm <sup>3</sup> | 1.8 - 2.0       |
| <b>Mechanical properties</b> |             |                     |                 |
| Hardness                     | ASTM D1706  | Shore D             | 56 - 60         |
| Tensile Strength (23°C)      | ASTM D1457  | N/mm <sup>2</sup>   | >7              |
| Elongation at Break          | ASTM D1457* | %                   | >150            |
| <b>Thermal properties</b>    |             |                     |                 |
| Service Temperature          |             | °C                  | -200 to +260    |

\*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Release: 20/09/2023  
 PIM-ID: 709616 • PIM-Code: 37-40-143.24-9.7.8.5.5.27.5.10-2  
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

