

Technical Data Sheet

Polystone[®] M AST + FDA black pressed

PE-UHMW / PE 1000

Typical characteristics

- Reduction of dust deposit
- Antistatic
- Good wear resistance
- Good impact strength

Typical industries

- Tecnologia di trasporto e automazione
- Ingegneria meccanica e impiantistica
- lavorazione carne, pesce e pollame
- Prodotti da forno o dolciari
- Industria delle bevande

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,94
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Molecular weight	-	10 ⁶ g/mol	~ 9
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	>20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>700
Notched impact strength	DIN EN ISO 11542	kJ / m ²	>50
Shore hardness	DIN EN ISO 868	scale D	>63
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-150 ... 80
Service temperature, short term (max.)	Average	°C	130
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$10^9 \dots 10^{11}$
Surface resistivity	DIN EN 62631-3-2	Ω	$10^9 \dots 10^{11}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 22/06/2026 • Release: 09/06/2026 • Version: 3.0
 PIM-ID: 591219 • PIM-Code: 1177-19-10.16.143.162-11.5.5.5.6-5
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

