

Technical Data Sheet

Fibracon[®] PTFE + 40% Bronze green

PTFE

Typical characteristics

- Conductividad térmica y eléctrica mejorada.
- Resistencia química reducida
- Deformación reducida bajo carga.

	Test method	Unit	Guideline value
Mechanical properties			
Hardness	Needle	Shore D	60-64
Tensile Strength	ASTM D4894	MPa	26
Elongation	ASTM D4894	%	250
Thermal properties			
Service Temperature		°C	-200 to +260

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 21/06/2026 • Release: 20/09/2023
 PIM-ID: 709621 • PIM-Code: 25-40-16.13.14
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

