

Technical Data Sheet

Polystone[®] E natural extruded

PE-LD

Typical characteristics

- Easy processing
- High flexibility
- High elongation at break
- Good impact strength

Typical industries

- 기계 공학 산업
- Healthcare
- Vacuum Forming

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	0,92
Water absorption	DIN EN ISO 62	%	0,1
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>200
Notched impact strength	DIN EN ISO 179	kJ / m ²	>60
Shore hardness	DIN EN ISO 868	scale D	>40
Thermal properties			
Melting temperature	ISO 11357-3	°C	105 ... 115
Thermal conductivity	DIN 52612-1	W / (m * K)	0,35
Thermal capacity	DIN 52612	kJ / (kg * K)	2,10
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-50 ... 60
Service temperature, short term (max.)	Average	°C	90
Electrical properties			
Dielectric constant	IEC 60250		2,4
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,0006
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹⁴

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 17/05/2026 • Release: 24/09/2025 • Version: 1.0
PIM-ID: 591123 • PIM-Code: 1181-8-12.12.11.162-5.27.4-5
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

