

### Technical Data Sheet

## Sustason<sup>®</sup> PPSU MG (Radel<sup>®</sup> R5500) blue - ASTM

PPSU

#### Typical characteristics

- Good sterilisation resistance
- High heat deflection temperature
- ISO 10993-5 tested on semi-finished product
- Chemical resistant
- High resistance to gamma and x-rays

#### Typical industries

- Healthcare
- Surgery

|   | Test method | Unit                       | Guideline value |
|---|-------------|----------------------------|-----------------|
| <b>General properties</b>               |             |                            |                 |
| Density                                 | ASTM D792   | g / cm <sup>3</sup>        | 1.29            |
| Water Absorption 24 hours               | ASTM D570   | %                          | 0.37            |
| Water Absorption Saturation             | ASTM D570   | %                          | 1.1             |
| <b>Mechanical properties</b>            |             |                            |                 |
| Hardness                                | ASTM D2240  | Shore D                    | 80              |
| Tensile Strength at yield 73°F          | ASTM D638   | psi                        | 11000           |
| Tensile Modulus                         | ASTM D638   | psi                        | 390000          |
| Elongation at Break                     | ASTM D638   | %                          | 30              |
| Flexural Strength                       | ASTM D790   | psi                        | 15500           |
| Flexural Modulus                        | ASTM D790   | psi                        | 350000          |
| Compressive Strength                    | ASTM D695   | psi                        | 14000           |
| Rockwell Hardness                       | ASTM D785   | M                          | 80              |
| Rockwell Hardness                       | ASTM D785   | R                          | 120             |
| Izod Impact, Notched                    | ASTM D256   | ft-lb/in                   | 13              |
| <b>Thermal properties</b>               |             |                            |                 |
| Thermal Conductivity                    |             | in/hr/ft <sup>2</sup> /F°  | 2.42            |
| Coefficient of Linear Thermal Expansion | ASTM D696   | in/in/°F x10 <sup>-5</sup> | 3.1             |
| Melting Point                           | ASTM D789   | °F                         | 424             |

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



|   | Test method | Unit | Guideline value  |
|---|-------------|------|------------------|
| Continuous Service Temperature, Air       |             | °F   | 320              |
| Deflection Temperature at 1.8Mpa (264psi) | ASTM D648   | °F   | 420              |
| Deflection Temperature at 1.8Mpa (66psi)  | ASTM D648   | °F   | 417              |
| <b>Electrical properties</b>              |             |      |                  |
| Surface resistivity                       | ASTM D257   | Ω/cm | 10 <sup>16</sup> |
| <b>Compliance properties</b>              |             |      |                  |
| FDA                                       |             |      | Yes              |
| NSF                                       |             |      | No               |
| USDA                                      |             |      | Yes              |

This material is not intended for the use in medical products that remain for more than 24 hours in the human body or are intended to remain in contact with internal human tissue or blood for more than 24 hours. The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5,000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 04/06/2026 • Release: 08/11/2024 • Version: 1.0  
 PIM-ID: 774124 • PIM-Code: 43-15-21.11.19.33.24-27.9-7  
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

