

Technical Data Sheet

Fibracon[®] PTFE + 60% Bronze

PTFE

Typical characteristics

- Improved thermal and electrical conductivity
- Reduced chemical resistance
- Reduced deformation under load

Typical industries

- Costruzione di serbatoi e impianti chimici
- Costruzione di veicoli
- Elettronica
- Olio e gas
- Ingegneria meccanica e impiantistica
- Healthcare
- Industria alimentare
- Energia eolica

	Test method	Unit	Guideline value
General properties			
Density	ASTM D1457	g / cm ³	3.8 - 4.0
Mechanical properties			
Hardness	ASTM D1706	Shore D	60 - 64
Tensile Strength (23°C)	ASTM D1457	N/mm ²	>12
Elongation at Break	ASTM D1457*	%	>80
Thermal properties			
Service Temperature		°C	-200 to +260

*12mm initial gauge used. This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 16/06/2026 • Release: 20/09/2023
 PIM-ID: 709626 • PIM-Code: 36-40-16.13.14-9.7.8.5.5.27.5.10-2
 Company-IDs: 21220

Page 1 / 1 (Dates in DD/MM/YYYY)

