

## Technical Data Sheet

# Maywoflamm<sup>®</sup> plus SPX

PC

### Typical characteristics

- Certified according to EN 45545-2

### Typical industries

- Vacuum Forming
- Rail Technology and Vehicles

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,30
Flammability	EN 45545		HL3 (R1, R6 - 2-6mm)
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	55
Elongation at break	DIN EN ISO 527	%	31
Tensile modulus of elasticity	DIN EN ISO 527	MPa	3925
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	22
Bending strength	DIN EN ISO 178	MPa	91
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	> 220 °C
Thermal conductivity	DIN 52612-1	W / (m * K)	0,2
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	65
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	108
<b>Electrical properties</b>			
Surface resistivity	DIN EN 61340	Ω	> 10 <sup>12</sup>
Volume resistivity	DIN EN 61340	Ω	> 10 <sup>12</sup>

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 14/06/2026 • Release: 08/04/2025 • Version: 6.0  
 PIM-ID: 751427 • PIM-Code: 45-7-16-4.11-12  
 Company-IDs: 20070

Page 1 / 1 (Dates in DD/MM/YYYY)

