

## Technical Data Sheet

# Laminex<sup>®</sup> 2100

### Typical characteristics

- Electrically insulating

### Typical industries

- Mechanical Engineering Industry

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	~1,40
<b>Mechanical properties</b>			
Bending strength	DIN EN ISO 178	MPa	80-150
Tensile modulus of elasticity	DIN EN ISO 527	MPa	5300-7200
Tensile modulus of bending	DIN EN ISO 178	MPa	5000-8200
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	10-14
Elongation at break	DIN EN ISO 527	%	1,3-3,5

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 26/05/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 715329 • PIM-Code: 41-24-13-5  
 Company-IDs: 20220

Page 1 / 1 (Dates in DD/MM/YYYY)

