

テクニカルデータシート

Robadur[®] OS

PE-UHMW / PE 1000

製品の特徴

- UV耐性
- 優れた滑り特性
- 非常に優れた耐摩耗性
- 酸化抑制作用
- 低比重
- 耐薬品性
- 高い耐衝撃性
- 高い剛性

製品の用途例

- 製紙

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	0,93
吸水率	DIN EN ISO 62	%	0,01
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB / HB
分子量		g/mol	9,2 * 10 ⁶
色			black
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	19
引張破壊呼び歪	DIN EN ISO 527	%	>200
引張弾性率	DIN EN ISO 527	MPa	540
ノッチ付き衝撃耐性	DIN EN ISO 179/1eA	kJ / m ²	>90
シヨア硬度	DIN EN ISO 868 / 15 sec	scale D	63
熱的物性			
融点	DIN EN ISO 3146	°C	135
熱伝導率	DIN EN ISO 8302	W / (m * K)	0,41
熱容量	DIN 51005	kJ / (kg * K)	1,84
線膨張係数	DIN 53752	10 ⁻⁶ / K	200
使用温度 (長期)	平均値	°C	-250 ... 90

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 25/05/2026 • Release: 20/09/2023 • Version: 1.0
PIM-ID: 709730 • PIM-Code: 48-11-15.223.126.9.17.33.18.132-8-6
Company-IDs: 21510


Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
使用温度 (短期、最大)	平均値	°C	110
電気的物性			
体積固有抵抗	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	10^{10}
表面固有抵抗	DIN EN 62631-3-2	Ω	10^{10}
比較トラッキング指数	IEC 60112		600

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

Chemical properties: chemically resistant to all aggressive media with the exception of highly oxidising acids. High resistant to corrosion. This material is resistant to all standard chemicals used in paper production, felt/wire cleaning and corrosion inhibition.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 25/05/2026 • Release: 20/09/2023 • Version: 1.0
PIM-ID: 709730 • PIM-Code: 48-11-15.223.126.9.17.33.18.132-8-6
Company-IDs: 21510

Page 2 / 2 (Dates in DD/MM/YYYY)

