

テクニカルデータシート

Polystone[®] MK FL + AST black extruded

PE-UHMW / PE 1000

製品の特徴

- EN 45545-2に準拠
- 自己消化性
- 帯電防止性

製品の用途例

- 機械工学
- 車両建造

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	>1,0
吸水率	DIN EN ISO 62	%	<0,1
燃焼性 (厚み 3 mm / 6 mm)	UL 94		V0
分子量	-	10 ⁶ g/mol	~ 9
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	>20
引張弾性率	DIN EN ISO 527	MPa	>1000
ショア硬度	DIN EN ISO 868	scale D	>63
熱的物性			
融点	ISO 11357-3	°C	130 ... 135
線膨張係数	DIN 53752	10 ⁻⁶ / K	150 ... 230
使用温度 (長期)	平均値	°C	-200 ... 80
使用温度 (短期、最大)	平均値	°C	130
ピカットB軟化温度	DIN EN ISO 306, Vicat B	°C	79
電気的物性			
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	10 ⁹ ... 10 ¹¹
表面固有抵抗	DIN EN 62631-3-2	Ω	10 ⁹ ... 10 ¹¹

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 19/06/2026 • Release: 09/06/2026 • Version: 4.0
 PIM-ID: 718531 • PIM-Code: 1077-26-16.12.16-5.7-5
 Company-IDs: 20000-1

Page 1 / 1 (Dates in DD/MM/YYYY)

