

## Technical Data Sheet

# Polystone<sup>®</sup> P EL black

PP

### Typical characteristics

- Electrically conductive

### Typical industries

- Construction de réservoirs et d'installations chimiques
- Stations de purification d'air
- Systèmes de ventilation
- Industrie de l'équipement électrique

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	20
Elongation at break	DIN EN ISO 527	%	74
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1400
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	15
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	165
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	<10 <sup>5</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	<10 <sup>5</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Release: 09/06/2026 • Version: 3.0

PIM-ID: 591334 • PIM-Code: 1104-6-13-9.4.4.11-5

Company-IDs: 20000-1

Page 1 / 1 (Dates in DD/MM/YYYY)

