

Technical Data Sheet

Durostone[®] EPF S1

GFK-EP

Typical industries

- Generator and Motor
- Oil-filled transformers
- Dry transformers
- Electrical Industry
- Electrical Insulating Components

	Test method	Unit	Guideline value
Mechanical properties			
Density	ISO 1183	g / cm ³	1,85
Flexural strength [⊥]	ISO 178	MPa	340
Modulus of elasticity in flexion [⊥]	ISO 178	MPa	24000
Compressive strength [⊥]	ISO 604	MPa	350
Compressive strength II	ISO 604	MPa	180
Tensile strength II	ISO 527	MPa	300
Impact strength II (Charpy)	ISO 179	kJ / m ²	50
Shear strength II	IEC 60893	MPa	30
Thermal properties			
Temperature index	IEC 60216	T.I.	155
Insulation class	IEC 60085	/	F
Physical properties			
Water absorption (4mm thickness)	ISO 62	%	< 0,1
Dielectrical properties			
Electric strength 90°C under oil [⊥]	IEC 60243	kV / mm	10
Electric strength 90°C under oil II	IEC 60243	kV/25mm	35
Relative permittivity (1 MHz)	IEC 60250	ε _r	5,5
Dielectric loss factor (50 Hz)	IEC 60250	tan δ	0,04
Comparative tracking index	IEC 60112	CTI	180

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Insulation resistance after 24 h water immersion	IEC 60167	Ω	5×10^{10}

⊥ = perpendicular to the lamination || = parallel to the lamination

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: www.roechling-industrial.com/gtc



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 20/09/2023 • Version: 1.0
 PIM-ID: 716634 • PIM-Code: 1071-30-4.6.6.11.7-13
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

