

## テクニカルデータシート

Trovidur<sup>®</sup> PVC-U white

PVC-U

## 製品の特徴

- 耐火性
- 自己消火性
- 高剛性
- 電気絶縁性
- 酸、塩類、塩類溶液に対する高い耐薬品性
- 良好な溶接性
- 優れた熱成形性
- Good glueability
- 非常に優れた印刷適性
- 耐薬品性

## 製品の用途例

- エレクトロニクス
- 化学産業
- ケミカルタンク

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,45
燃焼性 (厚み 3 mm / 6 mm)	UL 94		V0 / V0
<b>機械的物性</b>			
引張降伏応力	DIN EN ISO 527	MPa	45
引張破壊呼び歪	DIN EN ISO 527	%	15
引張弾性率	DIN EN ISO 527	MPa	3000
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m <sup>2</sup>	2
シヨア硬度	DIN EN ISO 868	scale D	79
<b>熱的物性</b>			
熱伝導率	DIN 52612-1	W / (m * K)	0,2
線膨張係数	DIN 53752	10 <sup>-6</sup> / K	80
使用温度 (長期)	平均値	°C	0 ... 60
使用温度 (短期、最大)	平均値	°C	70
<b>電氣的物性</b>			
誘電率	IEC 60250		3

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/06/2026 • Release: 05/05/2025 • Version: 1.0  
PIM-ID: 591337 • PIM-Code: 1104-18-16.11.11.13.20.16.34.3.17.33-8.9-7.6  
Company-IDs: 29033

Page 1 / 2 (Dates in DD/MM/YYYY)



	試験法	単位	値
誘電正接 (10 <sup>6</sup> Hz)	IEC 60250		0,02
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	10 <sup>15</sup>
表面固有抵抗	DIN EN 62631-3-2	Ω	10 <sup>13</sup>

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/06/2026 • Release: 05/05/2025 • Version: 1.0  
 PIM-ID: 591337 • PIM-Code: 1104-18-16.11.11.13.20.16.34.3.17.33-8.9.7-6  
 Company-IDs: 29033

Page 2 / 2 (Dates in DD/MM/YYYY)

