

### Technical Data Sheet

## Polystone<sup>®</sup> M Slide + AST grey

PE-UHMW / PE 1000

#### Typical characteristics

- Bajo coeficiente de fricción
- Alta resistencia a la abrasión
- Anti estático
- Autolubrificante
- Reducción de ruido
- resistente a los rayos UV

#### Typical industries

- Construcción de máquinas e instalaciones
- Sistemas de transporte y automatización
- Industria alimentaria

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Molecular weight	-	10 <sup>6</sup> g/mol	~ 9
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>600
Notched impact strength	DIN EN ISO 11542	kJ / m <sup>2</sup>	>110
Shore hardness	DIN EN ISO 868	scale D	>60
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
Service temperature, long term	Average	°C	-250 ... 80
Service temperature, short term (max.)	Average	°C	130
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
<b>Electrical properties</b>			

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/06/2026 • Release: 09/06/2026 • Version: 3.0  
 PIM-ID: 710139 • PIM-Code: 1100-21-12.63.16.10.13.15-5.11.5-5  
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$10^9 \dots 10^{11}$
Surface resistivity	DIN EN 62631-3-2	$\Omega$	$10^9 \dots 10^{11}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/06/2026 • Release: 09/06/2026 • Version: 3.0  
PIM-ID: 710139 • PIM-Code: 1100-21-12.63.16.10.13.15-5.11.5-5  
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

