

Technical Data Sheet

Polystone® PPs EL black pressed

PP-H

Typical characteristics

- Retardante de llama
- Anti estático
- Conducto electrico

Typical industries

- Electrónica
- Construcción de contenedores químico
- Sistemas de ventilación
- Sistemas de depuración de humos

| | Test method | Unit | Guideline value |
|-----------------------------------------|-------------------------|----------------------|------------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | >1,25 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | V0 |
| Mechanical properties | | | |
| Yield stress | DIN EN ISO 527 | MPa | >20 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >1300 |
| Notched impact strength | DIN EN ISO 179 | kJ / m ² | >4 |
| Shore hardness | DIN EN ISO 868 | scale D | >65 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | >145 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,22 |
| Thermal capacity | DIN 52612 | kJ / (kg * K) | 1,70 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 120 ... 190 |
| Service temperature, long term | Average | °C | 0 ... 100 |
| Service temperature, short term (max.) | Average | °C | 130 |
| Vicat softening temperature | DIN EN ISO 306, Vicat B | °C | 81 |
| Electrical properties | | | |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | <10 ⁵ |
| Surface resistivity | DIN EN 62631-3-2 | Ω | <10 ⁵ |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 05/01/2026 • Version: 5.0
 PIM-ID: 591141 • PIM-Code: 1111-41-16.16.13-8.9.4.4-5.8
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



Formulation is optimised for use in low-stress (square) pipeline construction.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 14/06/2026 • Release: 05/01/2026 • Version: 5.0
PIM-ID: 591141 • PIM-Code: 1111-41-16.16.13-8.9.4.4-5.8
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

