

Technical Data Sheet

LubX[®] CV - ASTM

PE-UHMW / PE 1000

Typical characteristics

- Good dry-running properties
- Good wear resistance
- Good machinability

Typical industries

- Beverage Industry
- Conveyor Technology & Automation
- Food Industry

	Test method	Unit	Guideline value
General properties			
Water Absorption	ASTM D570	%	0.01
Mechanical properties			
Hardness	ASTM D2240	Shore D	60
Tensile Strength at yield 73°F	ASTM D638	psi	2700
Elongation at Break	ASTM D638	%	>250
Thermal properties			
CTE, linear	ASTM D696	1/K	1.0x10 ⁻⁴
Melting Point		°F	275
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	108
Flammability, UL94		1/8 inch	HB
Electrical properties			
Volume Resistivity	ASTM D257	Ωcm	>10 ¹⁴
Surface resistivity	ASTM D257	Ω/cm	≥10 ¹²
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 04/06/2026 • Release: 08/04/2024 • Version: 1.0
 PIM-ID: 717942 • PIM-Code: 45-11-18.143.70-6.11.5-2
 Company-IDs: 23070

Page 1 / 1 (Dates in DD/MM/YYYY)

