

### Technical Data Sheet

## Polystone<sup>®</sup> G EL black extruded

PE-HD / PE 300

#### Typical characteristics

- Good weldability
- Easy processing
- Chemical resistant
- Good mechanical properties

#### Typical industries

- Construction de réservoirs et d'installations chimiques

|   | Test method             | Unit                 | Guideline value  |
|---|-------------------------|----------------------|------------------|
| <b>General properties</b>               |                         |                      |                  |
| Densité                                 | DIN EN ISO 1183-1       | g / cm <sup>3</sup>  | >0,98            |
| Water absorption                        | DIN EN ISO 62           | %                    | <0,01            |
| Flammability (Thickness 3 mm / 6 mm)    | UL 94                   |                      | HB               |
| Flammability (Thickness 3 - 10 mm)      | DIN 4102                |                      | B2               |
| <b>Mechanical properties</b>            |                         |                      |                  |
| Yield stress                            | DIN EN ISO 527          | MPa                  | >22              |
| Tensile modulus of elasticity           | DIN EN ISO 527          | MPa                  | >1100            |
| Notched impact strength                 | DIN EN ISO 179          | kJ / m <sup>2</sup>  | >5               |
| Shore hardness                          | DIN EN ISO 868          | scale D              | >65              |
| <b>Thermal properties</b>               |                         |                      |                  |
| Melting temperature                     | ISO 11357-3             | °C                   | 130 ... 135      |
| Coefficient of linear thermal expansion | DIN 53752               | 10 <sup>-6</sup> / K | 150 ... 230      |
| Service temperature, long term          | Average                 | °C                   | -50 ... 80       |
| Service temperature, short term (max.)  | Average                 | °C                   | 100              |
| Vicat softening temperature             | DIN EN ISO 306, Vicat B | °C                   | 67               |
| Thermal conductivity                    | DIN EN ISO 22007-2      | W / (m * K)          | 0,40             |
| Thermal capacity                        | DIN EN ISO 11357-4      | kJ / (kg * K)        | 1,90             |
| <b>Electrical properties</b>            |                         |                      |                  |
| Volume resistivity                      | DIN EN 62631-3-1        | Ω * cm               | <10 <sup>5</sup> |
| Surface resistivity                     | DIN EN 62631-3-2        | Ω                    | <10 <sup>5</sup> |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 22/06/2026 • Release: 20/09/2023 • Version: 1.0

PIM-ID: 591147 • PIM-Code: 1105-24-16.12.33.17-9-5

Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)





[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 22/06/2026 • Release: 20/09/2023 • Version: 1.0  
PIM-ID: 591147 • PIM-Code: 1105-24-16.12.33.17-9-5  
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

