

Technical Data Sheet

Robaseal[®] A

Rubber Graphite

Typical characteristics

- Good dry-running properties
- Low thermal expansion
- Good sliding properties

Typical industries

- Paper Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,57
Water absorption	DIN EN ISO 62	%	0,05
Approval			recommended operation time < 2 years
Coefficient of friction (against steel)	internal method: 2m/s; 1MPa	-	0,125
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	0,76
Tensile modulus of elasticity	DIN EN ISO 527	MPa	14.700
Tensile strength	DIN EN ISO 527	MPa	66
Shore hardness	DIN EN ISO 868 / 15 sec	scale D	~76
Flexural Strength		MPa	93
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	10,4
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	13,6
Service temperature, long term	Average	°C	120

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 16/10/2026 • Release: 16/04/2026 • Version: 2.0
PIM-ID: 709748 • PIM-Code: 70-3-18.12.223-8-4
Company-IDs: 21510

Page 1 / 1 (Dates in DD/MM/YYYY)

