

Technical Data Sheet

Polystone[®] M UV-stabilized - ASTM

PE-UHMW / PE 1000

Typical characteristics

- Extended life in outdoor locations
- Good wear properties
- Good impact strength
- UV-resistant

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	0.93
Water Absorption	ASTM D570	%	0.01
Mechanical properties			
Wear resistance	Sand-slurry		100
Hardness	ASTM D2240	Shore D	63
Tensile Strength at yield 73°F	ASTM D638	psi	3000
Tensile Modulus	ASTM D638	psi	100000
Elongation at Break	ASTM D638	%	>290
Flexural Strength	ASTM D790	psi	3200
Compressive Strength	ASTM D695	psi	2900
Coefficient of Friction, Dynamic			0.10-0.22
Coefficient of Friction, Static			0.15-0.20
Thermal properties			
CTE, linear	ASTM D696	1/K	1.1 x 10 ⁻⁴
Melting Point		°F	266 - 275
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	108
Flammability, UL94		1/8 inch	HB
Electrical properties			
Dielectric constant	ASTM D150	1MHz	2.3

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 04/06/2026 • Release: 20/09/2023
 PIM-ID: 717950 • PIM-Code: 31-19-12.126.162.15-2
 Company-IDs: 23070

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Surface resistivity	ASTM D257	Ω/cm	10 ⁴ - 10 ⁹
Compliance properties			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 04/06/2026 • Release: 20/09/2023
 PIM-ID: 717950 • PIM-Code: 31-19-12.126.162.15-2
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

