

## Technical Data Sheet

# Robaseal<sup>®</sup> S

Rubber Graphite

### Typical characteristics

- Good dry-running properties
- Low thermal expansion
- Good sliding properties even at higher load

### Typical industries

- Paper Industry

|   | Test method                 | Unit                 | Guideline value                    |
|---|-----------------------------|----------------------|------------------------------------|
| <b>General properties</b>               |                             |                      |                                    |
| Density                                 | DIN EN ISO 1183-1           | g / cm <sup>3</sup>  | 1,54                               |
| Water absorption                        | DIN EN ISO 62               | %                    | 0,05                               |
| Approval                                |                             |                      | recommended operation time 2 years |
| Coefficient of friction (against steel) | internal method: 2m/s; 1MPa | -                    | 0,11                               |
| <b>Mechanical properties</b>            |                             |                      |                                    |
| Elongation at break                     | DIN EN ISO 527              | %                    | 0,26                               |
| Tensile modulus of elasticity           | DIN EN ISO 527              | MPa                  | 13.500                             |
| Tensile strength                        | DIN EN ISO 527              | MPa                  | 43                                 |
| Shore hardness                          | DIN EN ISO 868 / 15 sec     | scale D              | 65                                 |
| Flexural Strength                       |                             | MPa                  | 71                                 |
| <b>Thermal properties</b>               |                             |                      |                                    |
| Thermal conductivity                    | DIN 52612-1                 | W / (m * K)          | 2,13                               |
| Coefficient of linear thermal expansion | DIN 53752                   | 10 <sup>-6</sup> / K | 25                                 |
| Service temperature, long term          | Average                     | °C                   | 140                                |

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 31/05/2026 • Release: 16/04/2026 • Version: 2.0  
 PIM-ID: 709750 • PIM-Code: 33-3-18.12.16-8-4  
 Company-IDs: 21510

Page 1 / 1 (Dates in DD/MM/YYYY)

