

Technical Data Sheet

Lamigamid[®] 304

PA 6 G

Typical characteristics

- Good sliding properties
- Insensitive to shock and vibration
- Good wear resistance

Typical industries

- Mechanical Engineering Industry
- Utility and special vehicles
- Alpine Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,13-1,14
Water absorption	DIN EN ISO 62	%	6,1-6,4
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	45-75
Elongation at break	DIN EN ISO 527	%	50-315
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1800-3300
Notched impact strength	DIN EN ISO 179	kJ / m ²	5-15
Thermal properties			
Melting temperature	ISO 11357-3	°C	205-225

All information correspond to the current state of our knowledge. The above mentioned values are ranges ascertained by statistical tests on a regular base. They display product information and should be used as guide only to choose from our range of materials. We do not ensure specific properties or suitabilities for particular applications. The material properties rely e.g. on the product dimension, thus the actual value of a particular product may differ from indicated values. Additional specific properties and values can be provided on request. Our material selection for a specific application is based on information by the customer. Despite given recommendation for applications by Röchling Industrial Xanten GmbH, the enduser is still liable to ensure that no third party is affected legally. Furthermore please refer to our general terms and conditions (AGB) <https://www.roechling.com/gtc>

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 31/05/2026 • Release: 20/09/2023 • Version: 2.0
 PIM-ID: 709654 • PIM-Code: 35-28-223.10.143-5,9,8-12
 Company-IDs: 20220

Page 1 / 1 (Dates in DD/MM/YYYY)

