

Technický datový list

Durostone[®] EPF S3

GFK-EP

Vlastnosti produktu

- EPGC 202 (IEC 60893)
- FR-4 (NEMA)

Typické oblasti použití

- Generátory a motory
- Olejové transformátory
- Suché transformátory
- Elektrotechnický průmysl
- Elektrické izolační konstrukční díly

	Testovací metoda	Jednotka	Orientační hodnota
Mechanické vlastnosti			
Hustota	ISO 1183	g / cm ³	1,90
Pevnost v ohybu [⊥]	ISO 178	MPa	540
Modul pružnosti v ohybu [⊥]	ISO 178	MPa	24000
Pevnost v tlaku [⊥]	ISO 604	MPa	580
Pevnost v tahu II	ISO 527	MPa	440
Rázová houževnatost II (Charpy)	ISO 179	kJ / m ²	90
Tepelné vlastnosti			
Hořlavost	UL 94	/	V0
Teplotní index	IEC 60216	T.I.	130
Izolační třída	IEC 60085	/	B
Fyzikální vlastnosti			
Absorpce vody	ISO 62	%	< 0,1
Dielektrické vlastnosti			
Elektrická pevnost 90 °C v olejové lázni [⊥]	IEC 60243	kV / mm	16
Elektrická pevnost 90 °C v olejové lázni II	IEC 60243	kV/25mm	60
Srovnávací sledovací index	IEC 60112	CTI	180
Izolační odolnost po 24 h ponoření do vody	IEC 60167	Ω	5 x 10 ¹²
Relativní permitivita (50 Hz / 1 MHz)	IEC 60250	ε _r	5
Dielektrický ztrátový činitel (50 Hz / 1 MHz)	IEC 60250	tan δ	0,01

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



L = perpendicular to the lamination II = parallel to the lamination

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: www.roechling-industrial.com/gtc



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 13/06/2026 • Vydáno: 02/09/2024 • Verze: 1.0
PIM-ID: 716656 • PIM-kód: 1071-30-9.9-4.6.6.11.7-13
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

