

Technical Data Sheet

Matrox[®] EX 60 black pressed

PE-UHMW / PE 1000

Typical characteristics

- Low coefficient of friction
- Good wear properties
- Antistatic

Typical industries

- Trasporto di merci sfuse

| | Test method | Unit | Guideline value |
|---|-------------------------|-----------------------|-----------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | >0,99 |
| Water absorption | DIN EN ISO 62 | % | 0,01 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Molecular weight | - | 10 ⁶ g/mol | ~ 9 |
| Mechanical properties | | | |
| Yield stress | DIN EN ISO 527 | MPa | >20 |
| Elongation at break | DIN EN ISO 527 | % | >50 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >900 |
| Notched impact strength | DIN EN ISO 11542-2 | kJ / m ² | >40 |
| Shore hardness | DIN EN ISO 868 | scale D | >63 |
| Wear resistance | Sand-slurry | | 100 |
| Sand Slurry | 1018 Steel=10 | | ~ 100 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 130 ... 135 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,41 |
| Thermal capacity | DIN 52612 | kJ / (kg * K) | 1,90 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 150 ... 230 |
| Service temperature, long term | Average | °C | -200 ... 80 |
| Service temperature, short term (max.) | Average | °C | 130 |
| Vicat softening temperature | DIN EN ISO 306, Vicat B | °C | 79 |
| Electrical properties | | | |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | 10 ⁹ |

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



| | Test method | Unit | Guideline value |
|---------------------|------------------|----------|-----------------|
| Surface resistivity | DIN EN 62631-3-2 | Ω | 10^9 |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 07/05/2026 • Release: 11/12/2024 • Version: 2.0

PIM-ID: 591159 • PIM-Code: 1093-41-12.126.16-6-5

Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

