

Technical Data Sheet

SustaECTFE natural

E-CTFE

Typical characteristics

- Flame retardant
- High purity
- High tensile strength
- High stiffness
- High cold impact strength
- High continuous service temperature
- Chemical resistant
- Good weather resistance

Typical industries

- Chemical Processing Industry
- Clean-Room Technology
- Electronics
- Bakery and Confectionery
- Chemical storage tanks
- Meat, Fish and Poultry Processing
- Food Industry

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,71
Flammability (Thickness 3 mm / 6 mm)	UL 94		V0 / V0
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	30
Elongation at break	DIN EN ISO 527	%	250
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1500
Shore hardness	DIN EN ISO 868	scale D	71
Thermal properties			
Melting temperature	ISO 11357-3	°C	230
Thermal conductivity	DIN 52612-1	W / (m * K)	0,15
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	90
Service temperature, long term	Average	°C	-50 ... 150
Service temperature, short term (max.)	Average	°C	180
Heat deflection temperature	DIN EN ISO 75, Verf. A, HDT	°C	70
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	10 ¹⁵
Surface resistivity	DIN EN 62631-3-2	Ω	10 ¹³

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 18/04/2025 • Release: 20/09/2023

PIM-Version: 985 • PIM-ID: 591381 • PIM-Code: 985-24-14.14.12.132.11.11.33.61-7.7.8.5.7.5.5-6

Company-IDs: 29033

Page 1 / 2 (Dates in DD/MM/YYYY)



	Test method	Unit	Guideline value
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	15

The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to a minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 18/04/2025 • Release: 20/09/2023

PIM-Version: 985 • PIM-ID: 591381 • PIM-Code: 985-24-14.14.12.132.11.11.33.61-7.7.8.5.7.5.5-6

Company-IDs: 29033

Page 2 / 2 (Dates in DD/MM/YYYY)

