

## Technical Data Sheet

# LubX<sup>®</sup> CV+ blue

PE-UHMW / PE 1000

### Typical characteristics

- Good sliding properties even at higher load
- Good machinability
- GMP 2023/2006 EC compliant

### Typical industries

- Construction de machines et d'installations
- Systèmes de convoyage et automatisation
- Industrie papetière
- Industrie agroalimentaire

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,94
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	>250
Tensile modulus of elasticity	DIN EN ISO 527	MPa	500
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	No break
Shore hardness	DIN EN ISO 868	scale D	60
Sliding partner POM MOD A (0,75 m/s - 0,25 MPa)	REP – Tribology – Test		0,12
Sliding partner POM MOD B (0,75 m/s - 0,25 MPa)	REP – Tribology – Test		0,13
Sliding partner PA MOD (0,75 m/s - 0,25 MPa)	REP – Tribology – Test		0,11
Sliding partner High steel grade (0,75 m/s - 0,25 MPa)	REP – Tribology – Test		0,17
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	133 ... 135
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
<b>Electrical properties</b>			

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
Volume resistivity	DIN EN 62631-3-1	$\Omega \cdot \text{cm}$	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	$\Omega$	$>10^{14}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/06/2026 • Release: 21/03/2025 • Version: 2.0  
PIM-ID: 774061 • PIM-Code: 522-42-16,70,15-5,11,8,5-5  
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

