

## Technický datový list

Lamigamid<sup>®</sup> 320

PA 6 G

## Vlastnosti produktu

- Good dimensional stability
- High hardness

## Typické oblasti použití

- Doprava sypkého materiálu
- Dopravní technika a automatizace

	Testovací metoda	Jednotka	Orientační hodnota
<b>Obecné vlastnosti</b>			
Hustota	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,13-1,17
<b>Mechanické vlastnosti</b>			
Mez kluzu	DIN EN ISO 527	MPa	70-85
Prodloužení při přetržení	DIN EN ISO 527	%	30-50
Modul pružnosti v tahu	DIN EN ISO 527	MPa	3000 - 4000
Vrubová houževnatost	DIN EN ISO 179	kJ / m <sup>2</sup>	4,5-9
<b>Tepelné vlastnosti</b>			
Teplota tání	ISO 11357-3	°C	220 - 230

All Information correspond to the current state of our knowledge. The above mentioned values are ranges ascertained by statistical tests on a regular base. They display product information and should be used as guide only to choose from our range of materials. We do not ensure specific properties or suitabilities for particular applications. The material properties rely e.g. on the product dimension, thus the actual value of a particular product may differ from indicated values. Additional specific properties and values can be provided on request. Our material selection for a specific application is based on information by the customer. Despite given recommendation for applications by Röchling Industrial Xanten GmbH, the enduser is still liable to ensure that no third party is affected legally. Furthermore please refer to our general terms and conditions (AGB) <https://www.roechling.com/gtc>

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 25/05/2026 • Vydáno: 20/09/2023 • Verze: 1.0  
PIM-ID: 709662 • PIM-kód: 26-28-153.11-6.11-12  
Company-IDs: 20220

Page 1 / 1 (Dates in DD/MM/YYYY)

