

## Technical Data Sheet

# Trovidur<sup>®</sup> EC Clad white

PVC-U

### Typical characteristics

- Protección contra incendios según EN 13501 B - s3, d0
- Buena resistencia al impacto
- buena soldabilidad
- Good glueability
- Resistencia química
- Procesamiento fácil

### Typical industries

- Sector de la construcción
- Tecnología de salas blancas
- Healthcare
- Industria alimentaria
- Construcción de contenedores químicos

|  | Test method             | Unit                | Guideline value |
|--|-------------------------|---------------------|-----------------|
| <b>General properties</b>                  |                         |                     |                 |
| Density                                    | DIN EN ISO 1183-1       | g / cm <sup>3</sup> | 1,44            |
| Water absorption                           | DIN EN ISO 62           | %                   | 0,2             |
| Flammability (Thickness 1 mm ... 3 mm)     | NF P 92-501             |                     | M1              |
| Flammability (Thickness 2,5 mm)            | BS 476 Part 6           |                     | Class 0         |
| Flammability (Thickness 2,5 mm)            | BS 476 Part 7           |                     | Class 1         |
| Flammability (Thickness 1,9 mm ... 2,5 mm) | EN 13501-1              |                     | B s3 d0         |
| Flammability (Thickness 1,7 mm ... 3 mm)   | UL 94                   |                     | V0              |
| <b>Mechanical properties</b>               |                         |                     |                 |
| Yield stress                               | DIN EN ISO 527          | MPa                 | 50              |
| Elongation at break                        | DIN EN ISO 527          | %                   | 20              |
| Tensile modulus of elasticity              | DIN EN ISO 527          | MPa                 | 2800            |
| Notched impact strength                    | DIN EN ISO 179          | kJ / m <sup>2</sup> | 4               |
| Shore hardness                             | DIN EN ISO 868          | scale D             | 80              |
| Ball Hardness                              | ISO 2039                | MPa                 | 110             |
| Compressive strength                       | DIN EN ISO 604          | MPa                 | 65              |
| Bending strength                           | DIN EN ISO 178          | MPa                 | 70              |
| <b>Thermal properties</b>                  |                         |                     |                 |
| Thermal conductivity                       | DIN 52612-1             | W / (m * K)         | 0,16            |
| Vicat softening temperature                | DIN EN ISO 306, Vicat B | °C                  | 75              |

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



|  | Test method        | Unit   | Guideline value   |
|--|--------------------|--------|-------------------|
| Service Temperature                                |                    | °C     | -15 ... +60       |
| Heat deflection temperature                        | DIN EN ISO 75      | °C     | 66                |
| Coefficient of linear thermal expansion            | DIN EN ISO 11359-2 | mm/m K | ~ 0,075           |
| <b>Electrical properties</b>                       |                    |        |                   |
| Dielectric constant                                | IEC 60250          |        | 3,20              |
| Dielectric dissipation factor (10 <sup>6</sup> Hz) | IEC 60250          |        | 0,02              |
| Volume resistivity                                 | DIN EN 62631-3-1   | Ω * cm | >10 <sup>15</sup> |
| Surface resistivity                                | DIN EN 62631-3-2   | Ω      | >10 <sup>13</sup> |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 07/05/2026 • Release: 10/10/2024 • Version: 1.0  
 PIM-ID: 591164 • PIM-Code: 1194-21-12.162.16.3.33.12-10.7.27.5.9-5  
 Company-IDs: 20000-2

Page 2 / 2 (Dates in DD/MM/YYYY)

