

## Technical Data Sheet

# Polystone<sup>®</sup> G HD SK black

PE-HD / PE 300

### Typical characteristics

- Good weldability
- Easy processing
- Chemical resistant
- Good mechanical properties
- High adhesion in a composite system

### Typical industries

- 화학 가공 산업
- 식수 및 폐수 처리 기술
- 화학물질 저장 탱크
- 기계 공학 산업
- Aquafarming
- Working and Recreational Boats
- 선박 및 보트 건조

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Flammability (Thickness 3 - 10 mm)	DIN 4102		B2
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>22
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	>10
Shore hardness	DIN EN ISO 868	scale D	>60
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
Service temperature, long term	Average	°C	-50 ... 80
Service temperature, short term (max.)	Average	°C	100
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	67

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



	Test method	Unit	Guideline value
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,4
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,0004
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>14</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	>10 <sup>14</sup>
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 16/06/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 750566 • PIM-Code: 35-13-16.12.33.17.12-9.6.7.5.5.11.4-5  
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

