

Technical Data Sheet

Sustarin[®] C FDA blue - ASTM

POM-C

Typical characteristics

- Good sliding properties
- Low moisture absorption
- Good dimensional stability
- Chemical resistant

Typical industries

- Food Industry
- Bakery and Confectionery
- Conveyor Technology & Automation

	Test method	Unit	Guideline value
General properties			
Density	ASTM D792	g / cm ³	1.41
Water Absorption 24 hours	ASTM D570	%	0.2
Dissipation Factor	ASTM D150	1MHz	0.004
Water Absorption Saturation	ASTM D570	%	0.9
Mechanical properties			
Hardness	ASTM D2240	Shore D	85
Tensile Strength at yield 73°F	ASTM D638	psi	9500
Tensile Modulus	ASTM D638	psi	400000
Compressive Strength	ASTM D695	psi	15000
Rockwell Hardness	ASTM D785	M	88
Rockwell Hardness	ASTM D785	R	120
Shear Strength	ASTM D732	psi	8000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.21
Thermal properties			
Thermal Conductivity		in/hr/ft ² /°F	1.6
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	5.5
Melting Point		°F	330
Continuous Service Temperature, Air		°F	180
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	225
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	320
Flammability, UL94		1/8 inch	HB

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



	Test method	Unit	Guideline value
Electrical properties			
Dielectric constant	ASTM D150	1MHz	3.8
Dielectric strength	ASTM D149	V/mil	450
Surface resistivity	ASTM D257	Ω/cm	10^{16}
Compliance properties			
FDA			Yes
NSF			No
USDA			Yes



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 04/06/2026 • Release: 13/04/2026 • Version: 1.0
 PIM-ID: 776166 • PIM-Code: 45-15-223.12.153.33-5.5.11
 Company-IDs: 23070

Page 2 / 2 (Dates in DD/MM/YYYY)

