

Technical Data Sheet

Polystone[®] M yellow pressed

PE-UHMW / PE 1000

Typical characteristics

- Low coefficient of friction
- Good impact strength
- Good wear properties

Typical industries

- Ingegneria meccanica e impiantistica
- Sport e tempo libero
- Tecnologia di trasporto e automazione
- Industria alimentare

Sustainability

- LCA available (ISO 14040/44)

| | Test method | Unit | Guideline value |
|---|-------------------------|----------------------|-----------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | >0,93 |
| Water absorption | DIN EN ISO 62 | % | 0,01 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Molecular weight | | g/mol | ~ 9 |
| Mechanical properties | | | |
| Elongation at yield stress | DIN EN ISO 527 | % | >300 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >650 |
| Notched impact strength | DIN EN ISO 11542 | kJ / m ² | >100 |
| Shore hardness | DIN EN ISO 868 | scale D | >60 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 130 ... 135 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,40 |
| Thermal capacity | DIN 52612 | kJ / (kg * K) | 1,90 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 150 ... 230 |
| Service temperature, long term | Average | °C | -250 ... 80 |
| Service temperature, short term (max.) | Average | °C | 130 |
| Vicat softening temperature | DIN EN ISO 306, Vicat B | °C | 80 |
| Electrical properties | | | |
| Dielectric constant | IEC 60250 | | 2,3 |

ri-inquiry@roechling.com • www.roechling.com/industrial/materials



| | Test method | Unit | Guideline value |
|--|------------------|---------|-------------------|
| Dielectric dissipation factor (10 ⁶ Hz) | IEC 60250 | | 0,0001 |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | >10 ¹⁴ |
| Surface resistivity | DIN EN 62631-3-2 | Ω | >10 ¹⁴ |
| Comparative tracking index | IEC 60112 | | 600 |
| Dielectric strength | IEC 60243 | kV / mm | >40 |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 07/05/2026 • Release: 25/01/2024 • Version: 2.0
 PIM-ID: 746370 • PIM-Code: 1076-18-12.162.126-5.3.11.5-3-5
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

