

Technical Data Sheet

Formaterm[®] PS-HI sign/advertising

PS

Typical characteristics

- Alta resistencia al impacto
- Alta rigidez
- Muy bueno imprimible

Typical industries

- Construcción de vehículos
- Sector de la construcción
- Rotulación
- Construcción de buques y embarcaciones

| | Test method | Unit | Guideline value |
|--|-------------------------|----------------------|-------------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | 1,04 |
| Water absorption | DIN EN ISO 62 | % | 0,2 – 0,3 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Mechanical properties | | | |
| Yield stress | DIN EN ISO 527 | MPa | 21 |
| Elongation at break | DIN EN ISO 527 | % | 60 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | 1850 |
| Notched impact strength | DIN EN ISO 179 | kJ / m ² | 10 |
| Shore hardness | DIN EN ISO 868 | scale D | 80 |
| Thermal properties | | | |
| Glass transition temperature | ISO 11357-3 | °C | 95 – 100 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,18 |
| Coefficient of linear thermal expansion | DIN 53752 | 10 ⁻⁶ / K | 70 |
| Service temperature, long term | Average | °C | -10 ... 80 |
| Service temperature, short term (max.) | Average | °C | 75 – 90 |
| Vicat softening temperature | DIN EN ISO 306, Vicat B | °C | 99 |
| Electrical properties | | | |
| Dielectric constant | IEC 60250 | | 2,50 |
| Dielectric dissipation factor (10 ⁶ Hz) | IEC 60250 | | 0,0004 |
| Volume resistivity | DIN EN 62631-3-1 | Ω * cm | >10 ¹⁶ |

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 27/03/2025 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 39 • PIM-ID: 709638 • PIM-Code: 39-14-18.132.14-7.10.9.5-5
 Company-IDs: 21630

Page 1 / 2 (Dates in DD/MM/YYYY)



| | Test method | Unit | Guideline value |
|---------------------|------------------|----------|-----------------|
| Surface resistivity | DIN EN 62631-3-2 | Ω | $>10^{15}$ |
| Dielectric strength | IEC 60243 | kV / mm | 40 |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 27/03/2025 • Release: 20/09/2023 • Version: 1.0
PIM-Version: 39 • PIM-ID: 709638 • PIM-Code: 39-14-18.132.14-7.10.9.5-5
Company-IDs: 21630

Page 2 / 2 (Dates in DD/MM/YYYY)

