

### Technical Data Sheet

## Maywoblend<sup>®</sup> PS/PE CR

#### Typical characteristics

- Soft-touch effect

#### Typical industries

- Vacuum Forming

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,0
Water absorption	DIN EN ISO 62	%	<0,1
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	11
Elongation at break	DIN EN ISO 527	%	>150
Tensile modulus of elasticity	DIN EN ISO 527	MPa	735
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	>170°C
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79,7
<b>Electrical properties</b>			
Surface resistivity	DIN EN 61340	Ohm	>10 <sup>12</sup>
Volume resistivity	DIN EN 61340	Ohm	>10 <sup>12</sup>

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

#### Röchling Industrial Allgäu GmbH

Hinter den Gärten 20 • 87730 Bad Grönenbach/Germany (DE) • Tel. +49 8334 9857-0  
[info@roechling-maywo.de](mailto:info@roechling-maywo.de) • [www.roechling.com/industrial/groenenbach](http://www.roechling.com/industrial/groenenbach)

Print: 27/04/2024 • Release: 20/09/2023 • Version: 1.0  
 PIM-Version: 39 • PIM-ID: 709680 • PIM-Code: 39-14-8-4-12

