

Technical Data Sheet

Robatube EPDM black

EPDM

Typical characteristics

- Chemical resistant
- Good stroke characteristics
- High temperature resistance

Typical industries

- 제지 산업

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,14
Water absorption	DIN EN ISO 62	%	0,74
Color			black
Storage period in years			~ 3
Mechanical properties			
Shore hardness	DIN EN ISO 868	scale A	60
Tensile strength	internal method	MPa	9,5
Max. pressure	internal method	bar	1,5
Burst pressure	internal method	bar	> 1,5
Elongation at break	internal method	%	> 400
Thermal properties			
Service temperature, long term	Average	°C	-35 ... 120

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

The burst pressure was determined at a temperature of 20°C (locular).

ri-inquiry@roechling.com • www.roechling.com/industrial/materials

Print: 12/12/2025 • Release: 20/09/2023 • Version: 2.0
 PIM-Version: 27 • PIM-ID: 709773 • PIM-Code: 27-3-33.10.11-8-2
 Company-IDs: 21510

Page 1 / 1 (Dates in DD/MM/YYYY)

