

## Technický datový list

## Maywosoft® ABS/TPU super matt

ABS / TPU

## Vlastnosti produktu

- Good thermoformability
- Mat surface
- Soft-touch effect

## Typické oblasti použití

- Technika hlubokého tažení

	Testovací metoda	Jednotka	Orientační hodnota
<b>Obecné vlastnosti</b>			
Hustota	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,08
Absorpce vody	DIN EN ISO 62	%	0,3
<b>Mechanické vlastnosti</b>			
Mez kluzu	DIN EN ISO 527	MPa	29
Prodloužení při přetržení	DIN EN ISO 527	%	33
Modul pružnosti v tahu	DIN EN ISO 527	MPa	1850
Vrubová houževnatost	DIN EN ISO 179	kJ / m <sup>2</sup>	9
<b>Teplné vlastnosti</b>			
Teplota tání	ISO 11357-3	°C	-
Teplota měknutí dle Vicata	DIN EN ISO 306, dle Vicata B	°C	97
<b>Elektrické vlastnosti</b>			
Objemový odpor	DIN EN 62631-3-1	Ω * cm	>10 <sup>12</sup>
Povrchový odpor	DIN EN 62631-3-2	Ω	>10 <sup>12</sup>

The information and recommendations contained in this document are based upon data collected by Röchling Industrial Allgäu and believed to be correct. However, no warranty of fitness for use or any other guarantees or warranty of any kind, expressed or implied, is made to the information contained herein. Röchling Industrial Allgäu assumes no responsibility for the results of the use of products and processes described herein.

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 15/06/2026 • Vydáno: 05/08/2024 • Verze: 5.0

PIM-ID: 709671 • PIM-kód: 97-12-34.17.9-4-12

Company-IDs: 20070

Page 1 / 1 (Dates in DD/MM/YYYY)

