

### Technical Data Sheet

## Play-Tec<sup>®</sup> UV-stabilized bicolor

PE-HD / PE 300

#### Typical characteristics

- Physiologically safe
- UV-stabilized
- Colourfast
- Good machinability
- UV-resistant

#### Typical industries

- Sport e tempo libero
- Costruzione di navi e imbarcazioni
- Parco giochi
- Imbarcazioni da lavoro e da diporto

|   | Test method             | Unit                 | Guideline value |
|---|-------------------------|----------------------|-----------------|
| <b>General properties</b>               |                         |                      |                 |
| Density                                 | DIN EN ISO 1183-1       | g / cm <sup>3</sup>  | >0,96           |
| Water absorption                        | DIN EN ISO 62           | %                    | 0,01            |
| Flammability (Thickness 3 mm / 6 mm)    | UL 94                   |                      | HB              |
| Flammability (Thickness 3 - 10 mm)      | DIN 4102                |                      | B2              |
| <b>Mechanical properties</b>            |                         |                      |                 |
| Yield stress                            | DIN EN ISO 527          | MPa                  | >23             |
| Elongation at break                     | DIN EN ISO 527          | %                    | >50             |
| Tensile modulus of elasticity           | DIN EN ISO 527          | MPa                  | >1100           |
| Notched impact strength                 | DIN EN ISO 179          | kJ / m <sup>2</sup>  | >10             |
| Shore hardness                          | DIN EN ISO 868          | scale D              | >60             |
| <b>Thermal properties</b>               |                         |                      |                 |
| Melting temperature                     | ISO 11357-3             | °C                   | 130 ... 135     |
| Thermal conductivity                    | DIN 52612-1             | W / (m * K)          | 0,40            |
| Thermal capacity                        | DIN 52612               | kJ / (kg * K)        | 1,90            |
| Coefficient of linear thermal expansion | DIN 53752               | 10 <sup>-6</sup> / K | 150 ... 230     |
| Service temperature, long term          | Average                 | °C                   | -30 ... 80      |
| Service temperature, short term (max.)  | Average                 | °C                   | 100             |
| Vicat softening temperature             | DIN EN ISO 306, Vicat B | °C                   | 67              |
| <b>Electrical properties</b>            |                         |                      |                 |
| Dielectric constant                     | IEC 60250               |                      | 2,4             |

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)



|  | Test method      | Unit    | Guideline value   |
|--|------------------|---------|-------------------|
| Dielectric dissipation factor (10 <sup>6</sup> Hz) | IEC 60250        |         | 0,0004            |
| Volume resistivity                                 | DIN EN 62631-3-1 | Ω * cm  | >10 <sup>14</sup> |
| Surface resistivity                                | DIN EN 62631-3-2 | Ω       | >10 <sup>14</sup> |
| Comparative tracking index                         | IEC 60112        |         | 600               |
| Dielectric strength                                | IEC 60243        | kV / mm | >40               |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 13/05/2026 • Release: 11/12/2024 • Version: 1.0  
 PIM-ID: 590974 • PIM-Code: 1111-63-11.9.3.70.15-3.5.8.11-5  
 Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

