

## Technical Data Sheet

# LubX<sup>®</sup> AST white

PE-UHMW / PE 1000

### Typical characteristics

- Anti estático
- Buenas propiedades de deslizamiento
- Excelentes propiedades de funcionamiento en seco
- Buena resistencia al desgaste

### Typical industries

- Construcción de máquinas e instalaciones
- Sistemas de transporte y automatización
- Industria alimentaria
- Productos de bollería y dulces
- Industria de bebidas

	Test method	Unit	Guideline value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	15
Elongation at yield stress	DIN EN ISO 527	%	23
Tensile modulus of elasticity	DIN EN ISO 527	MPa	510
Impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	50
Shore hardness	DIN EN ISO 868	scale D	60
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	133 - 135
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
<b>Electrical properties</b>			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	≤10 <sup>9</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	≤10 <sup>9</sup>

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 16/06/2026 • Release: 18/08/2025 • Version: 2.0  
 PIM-ID: 718574 • PIM-Code: 1074-8-16.223.18.143-5.11.5.5.6-5  
 Company-IDs: 20000-1

Page 1 / 2 (Dates in DD/MM/YYYY)



The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 16/06/2026 • Release: 18/08/2025 • Version: 2.0  
PIM-ID: 718574 • PIM-Code: 1074-8-16.223.18.143-5.11.5.5.6-5  
Company-IDs: 20000-1

Page 2 / 2 (Dates in DD/MM/YYYY)

