

## Technical Data Sheet

# Robatube PVC

PVC-U

### Typical characteristics

- Chemical resistant
- Good stroke characteristics
- High temperature resistance

### Typical industries

- Industrie papetière

	Test method	Unit	Guideline value
<b>General properties</b>			
Densité	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,21
Water absorption	DIN EN ISO 62	%	0,016
Couleur			violet
Storage period in years			~ 5
<b>Mechanical properties</b>			
Shore hardness	DIN EN ISO 868	scale A	58
Tensile strength	internal method	MPa	11
Max. pressure	internal method	bar	2,0
Burst pressure	internal method	bar	> 2,5
Elongation at break	internal method	%	400
<b>Thermal properties</b>			
Service temperature, long term	Average	°C	-45 ... 70

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved. The burst pressure was determined at a temperature of 20°C (locular).

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 02/06/2026 • Release: 20/09/2023 • Version: 1.0  
 PIM-ID: 709775 • PIM-Code: 27-11-33.10.11-8-2  
 Company-IDs: 21510

Page 1 / 1 (Dates in DD/MM/YYYY)

