

## テクニカルデータシート

## Robatube PVC

PVC-U

## 製品の特徴

- 耐薬品性
- 優れたストローク特性
- 高温耐性

## 製品の用途例

- 製紙

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	1,21
吸水率	DIN EN ISO 62	%	0,016
色			violet
保管期間			~ 5
<b>機械的物性</b>			
シヨア硬度	DIN EN ISO 868	scale A	58
引張強度	internal method	MPa	11
最大圧力	internal method	bar	2,0
バースト圧力	internal method	bar	> 2,5
引張破壊呼び歪	internal method	%	400
<b>熱的物性</b>			
使用温度 ( 長期 )	平均値	°C	-45 ... 70

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

The burst pressure was determined at a temperature of 20°C (ocular).

[ri-inquiry@roechling.com](mailto:ri-inquiry@roechling.com) • [www.roechling.com/industrial/materials](http://www.roechling.com/industrial/materials)

Print: 02/06/2026 • Release: 20/09/2023 • Version: 1.0

PIM-ID: 709775 • PIM-Code: 27-11-33.10.11-8-2

Company-IDs: 21510

Page 1 / 1 (Dates in DD/MM/YYYY)

